



DATA SHEET



PAINTING POOL ACRYLIC KOLMER PAPCAE

FEATURES		COLORS	CONTAINER	PACKAGING
<ul style="list-style-type: none"> • Paint made with acrylic dispersions in water. • Suitable for swimming pools and sports facilities. 		WHITE BLUE	4 liters	4 units for 4 liters
SURFACE	PREPARATION	DRYING	REPAINT	FINISH
CONCRETE, CEMENT	KOLMAN FIXATIVE SEALANT	2 HOURS	12 HOURS	SMOOTH MATT
THINNER	PERFORMANCE	DENSITY	WASHABILITY	SOLIDS CONTENT
UP 10% WATER	5-10 m ²	1.30 g/cc		62%

PROPERTIES

- Waterproof.
- High resistance to outside.
- High elasticity.
- Good performance.
- Resistant to alkalinity.
- Easy application
- Not toxic.
- Non-flammable.
- Does not yellow.
- High resistance to aging.
- It is made in white and blue.

INSTRUCTIONS

- It is imperative that the surfaces are perfectly clean, dry and in perfect adhesion.
- It can be applied on cements, concrete, artificial stone and on any paint that is perfectly adhered, sanded and with sufficient porosity to allow a good adhesion.
- On metal surfaces must be pre-primed.
- On dusty and / or inconsistent surfaces, apply previously KOLMAN FIXING SEALER.
- Apply a first coat of KOLMER ACRYLIC POOL PAINT diluted to 10% water. Wait a minimum of 12 hours to apply the second hand.
- Minimum curing time of the new concrete to be painted: 30 days.

SURFACE PREPARATION

Mortars and concretes:

Unpainted Surfaces: Wait for 30 days for proper solidification, clean efflorescence, release agents, mold and moss, loose particles and dirt. Whenever necessary, open pore by sanding polished surfaces. Before applying the finish coat, it is recommended to seal with KOLMAN FIXING SEALER or KOLMAN ANTICARBONATING PRINT, as required.

Already painted surfaces: Remove any old or poorly adhered paint. If the surface does not have good adhesion, it should be sanded and primed if necessary. If there are molds or moss, they must be treated and eliminated. Check the compatibility of the support and existing paint with the new paint to be applied.

Plaster and gypsum:

Unpainted surfaces: Wait for 30 days for proper solidification/drying. Sanitize and clean the support, eliminating efflorescence and loose particles. Apply a sealant, fixative or anti-carbonation primer, if necessary. If the support is good enough, a first coat of the diluted finishing layer may suffice.

Already painted surfaces: Remove any old or poorly adhered paint. If the surface does not have good adhesion, it should be sanded and primed if necessary. If there are efflorescence, molds or moss, they must be treated and eliminated. Check the compatibility of the support and existing paint with the new paint to be applied.

Ferrous metal surfaces:

Unpainted surfaces: On iron or steel supports, sand and clean with a cloth moistened with solvent to remove oils and grease, as well as rust residues. Next, apply a layer of antioxidant primer, and finish with the chosen varnish, unless an antioxidant varnish is used and the primer is not necessary.

Already painted surfaces: Remove any old or poorly adhered paint. If old paint has been removed, proceed as on new surfaces. If it has not been removed, check the compatibility of the existing paint with the one to be used.

Non-ferrous surfaces with difficult adhesion:

Unpainted surfaces: For surfaces such as aluminum, stainless steel, brass, galvanized, PVC ..., in addition to cleaning with a cloth moistened with solvent to remove oils and greases, you must treat them with a specific primer (wash primer, multi-adherent primer, etc.) and then apply the chosen finishing product or use a multi-adherent finishing product or with direct adhesion on this type of supports. In case of rust spots, it is necessary to treat specifically with an antioxidant primer. Check the compatibility of the latter with the surface and apply the necessary layers of product.

Already painted surfaces: Remove any old or poorly adhered paint. If the surface does not have good adhesion, it must be sanded and primed if necessary. If rust is present, treat it and remove loose particles. Check the compatibility of the support and the existing paint with the paint to be used.

Wood:

Unpainted Surfaces: When treating the wood, make sure that it is dry enough, as excess moisture will cause adhesion flaws and/or coloring flaws when dyeing the wood since the pores are filled with water. The moisture content should not exceed 12% -15%, depending on the type of wood. For new woods, remove stains and dirt, let dry if wet and then sand. Apply a priming coat or sealer, sand and later apply at least two layers of finish (it is recommended to sand between each layer). It is important to take into account the direction of the grain, both when sanding and applying, which must be done in the same direction.

Already painted surfaces: On painted wood, if the paint is very deteriorated, the easiest is to strip and remove the old paint. If the old paint is in good condition, sanding the surface is enough. It is recommended to perform a test, applying the paint in a small area, to ensure that there is no incompatibility between the two painting systems and the paintings themselves (e.g. old solvent paint and new water paint or vice versa). It is recommended to sand between each layer.

Tiles:

Clean and degrease the surface to be painted, eliminating all dirt and grease, and apply a specific paint for tiles directly, without primer. Always perform an adhesion test to verify the compatibility of the support with the paint.

Other surfaces:

For other special surfaces, please check.

Update date:

STORAGE

Protect the containers from extreme temperatures 0°C. / 40 °C.

Recommended storage time, no more than 2 years

ENVIRONMENT

Containers and waste must be disposed of according to current legislation. Do not throw waste into drains, consider possible reuse

SAFETY

Keep out of the reach of children.

Do not drink, eat, or smoke during application.

In case of contact with eyes, wash off with plenty of water.

For more information, please check the product safety data sheet.



Ambikol 2010:

Products under the Integral System of Quality, Environment and Prevention, ISO 9001 and ISO 14001.



PAPCAE:

Painting Applied Against External Agents. It prevents the appearance of mold and moss.



INDUSTRIAS KOLMER S.A

Polígono Industrial Juncaril, Calle Loja. Parcelas 111A-112.

Albolote. Granada. ESPAÑA

Phone: +34 958 46 56 86 || Fax: +34 958 46 74 02.

kolmer@kolmersa.com || www.kolmer.es

*Margin of numerical data: +-20%